

Typical Properties Chart

Product	Color	Density	Depth Rating	Hydrostatic Crush	Compressive Strength	Compressive Modulus	Shear Strength
		lb/ft ³ (g/cc)	feet (meters)	feet (meters)	psi (MPa)	ksi (GPa)	psi (MPa)
MacroFoam -18	Natural	18 ± 2.0 (0.29 ± .03)	1,000 (300)	1,485 (450)	1,200 (8)	65 (0.448)	625 (4)
MacroFoam - 20	White	20 ± 1.5 (0.32 ± .02)	1,650 (500)	2,485 (760)	1,700 (12)	78 (0.537)	750 (5)
MacroFoam - 22	Yellow	22 ± 1.5 (0.35 ± .02)	2,500 (750)	3,725 (1,135)	1,900 (13)	80 (0.550)	810 (6)
MacroFoam - 24	Red	24 ± 1.5 (0.39 ± .02)	3,280 (1,000)	4,968 (1,515)	2,100 (14)	82 (0.565)	900 (6)